

U.S. Coast Guard Felt

Maritime Insulation

- + Fire resistant to temperatures above 2,000°F (1,093°C)
- + Excellent thermal performance (R-Value up to 4.2 per inch)
- + Exceptional sound and noise absorption
- + Easily fabricated and installed
- + Moisture resistant
- + Mold resistant



Thermafiber U.S. Coast Guard Felt meets requirements for insulating structural bulkheads in vessels operating within all U.S.A. waters.

Minimum
70%
Recycled
Content



U.S. Coast Guard Felts are classified as noncombustible and have achieved fire resistance ratings. The semi-rigid boards are easy to fabricate and install.



Thermafiber[®]



Made in the USA

Thermafiber® U.S. Coast Guard Felt

Description:

THERMAFIBER U.S. Coast Guard Felt is available from 3.0 pcf to 9.0 pcf density, is highly suited for use on vessels operating within U.S.A. waters. Felts are classified noncombustible, have achieved fire-resistance ratings, and meet requirements for insulations impaled on structural bulkheads. These products are permanent, absorb less than 1% moisture, vermin-proof and mold resistant. They do not corrode steel or aluminum as tested per HH-I-558B.

Product Options:

Recycled Content Options¹:

- Dark Fiber84%
- EPA Choice Fiber (US Government).....75%
- Standard Fiber70%

¹Recycled content options other than Standard must be specified at time of order.

Installation:

The frequency, location and size of attachment points vary depending on the thickness of the insulation. For most applications, 12 SWG (Standard Wire Gauge) steel weld pins should be attached to the substrate and a minimum of 1 1/2" diameter round clinch shield should be used to hold the insulation in place on the pin. This type of weld pin is recommended because it resists fire exposure conditions. Pin spacing is normally 12" o.c., but spacing may be less than 12" o.c. for thicker insulations. When insulation thickness exceeds 5", 10 SWG steel weld pins should be used.

Standard Sizes:

Density	Thickness*	Widths**	Lengths**
3.0 pcf	1 1/2" - 7"	24", 36"	48", 60"
4.0 pcf - 6.0 pcf	1" - 7"	24", 36"	48", 60"
7.0 pcf - 8.0 pcf	1" - 5"	24", 36"	48", 60"
9.0 pcf	1" - 4"	24", 36"	48", 60"
Tolerances	+ 1/4" -1/8"	± 1/8"	± 1/2"

*Thicknesses are available in 1/2" increments. **Custom sizes are available upon request.

Technical Data:

Actual Density	Tested to ASTM C 518		Tested to ASTM E 84	
	"k" @ 75° [25°C] BTU.in/hr.sq. ft. °F	"R" value per inch of thickness***	Flame Spread	Smoke Developed
3.0 pcf	0.25	4.0	0	0
4.0 pcf - 9.0 pcf	0.24	4.2	0	0

***R = Thickness divided by 'k'

U.S. Coast Guard Specifications	
USCG Specification	Applicable Products
N & VI Circular C-680 A-15 (15 min.)	7.0 pcf, 1 1/2" thick
Standard 164.007/46/0 A-30 (30 min.)	6.0 pcf, 2" thick
Standard 164.007/40/0 A-60 (60 min.)	6.0 pcf, 4" thick 7.0 pcf, 2 1/2" thick
Standard 164.009/54	3.0 pcf - 9.0 pcf, all thicknesses

Based on the National Bureau of Standards fire test report FR 3812

Maximum Hot Surface Temperature One Side (enclosed panel) per ASTM C 411	
Density	Maximum °F
3.0 pcf	500
4.0 pcf - 9.0 pcf	1200

Note: Temperatures above 450° require mechanical support.

Standards Compliance:

MIL-I-24244A Meet applicable analysis for austenitic stainless steel
ASTM C665 Non-Corrosive, Type I
ASTM C 612 3.0 pcf IA ; 4.0-8.0 pcf IA, IB, II, III, IVA
ASTM C 612 9.0 pcf IA, IB, II, III, IVA, IVB
ASTM C 553 Type III
ASTM E 136 Rated Non-combustible per NFPA Standard 220 & IMO 164, 109/11/0
ASTM C 1104 Absorption less than 1% by volume
ASTM C 356 Linear shrinkage <2% @ 1200° F (650°C)

For Further Information:

For additional information about these or other Thermafiber products contact us at 1-888-834-2371 or visit our website www.thermafiber.com.

Notice:

THERMAFIBER, Inc. shall not be liable for incidental and consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instructions or for other than the intended use. THERMAFIBER liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing within thirty (30) days from date it was or reasonably should have been discovered.

Submittal Approvals:

Job Name	
Contractor	Date

